



TECHNICAL DATA

NP1025

HIGH THERMAL CONDUCTIVITY EPOXY RESIN SYSTEM

Product Description

NP1025 is a two part thermally conductive epoxy resin system with a low mix viscosity. The mixed system has a long pot life and can be cured at ambient or elevated temperatures. The flexibility of the resin and the very high filler loading make this system ideal for applications where temperature cycling and thermal stresses are encountered.

The LED Range of Resins

The NP1025 epoxy system provides state of the art thermal conductivity of over 1.3 W/m/⁰K from a liquid resin with a mix viscosity of 20 poise. The long (90 minutes) pot life allows users to further reduce this initial viscosity (to 1 – 2 poise) prior to use, by warming the resin. The penetration and wetting of substrates with this high thermally conductivity mix has allowed component manufacturers worldwide to push on the performance boundaries of their designs. The NP1025 epoxy resin system further provides outstanding electrical properties (e.g. 15 kV electric strength), very high flame retardancy, low cure shrinkage and thermal expansion coefficient (0.3% and 30 ppm/⁰C respectively).

Features

- * Very High Thermal Conductivity
- * Ambient or Elevated Temperature Dispensing and Curing
- * Contains No Halogens and is Non-Toxic.
- * Low Stress on Components

Applications

- * Assemblies
- * Power Supplies
- * Modules
- * Drivers



Typical Uncured Physical Properties

Property	Base	Hardener	Mixed System
Viscosity (mPas)	15000 – 30000	100	2000 - 4000
Colour	Grey	Clear	Grey
Specific Gravity	2.24 – 2.28	0.92 – 0.94	2.09 – 2.12
Mix Ratio	18 7.2	1 1	By Weight By Volume

Pot Life	90 Minutes	150 gm @ 23°C
Gel Time	6 Hours	150 gm @ 23°C
Peak Exotherm	+10 °C	150 gm @ 23°C
Complete Cure	24 Hours	150 gm @ 23°C

Typical Cured Properties

Property	Result	Units
Operating Temperature	-40 to +180	°C Continuous (Application & Geometry Dependent)
Shore D Hardness	76	
Electric Strength	15	kV/mm
Thermal Conductivity	1.3	W/m ⁰ K
Volume Resistivity	10 ¹⁴	Ohm-cm
Cure Shrinkage	0.3	% (volume)
Flammability	To UL 94 V-0 Level	Not Certified
Deflection Temperature	70	°C
Coefficient of Expansion	30	ppm/°C

Note: The above technical information and data should be considered representative or typical only and should not be used for specification purposes.



ALH Systems Limited

1 Kingdom Avenue, Northacre Industrial Park, Westbury, Wiltshire BA13 4WE England
Telephone: (+44) 01373 858234 Email: sales@alh-systems.co.uk



Supply	Details
Twinpacks	Ideal for mixing without the entrapment of air
Kits	The resin base and hardener are supplied in two separate containers, pre-weighed to facilitate accurate mixing for larger applications
Bulk	The NP1025 system is formulated to prevent sedimentation on storage. However, storage at higher ambient temperatures (above 25 °C for instance) or for long times, can cause some settlement. It is important that any sediment is redispersed into the bulk resin prior to using the resin. This can be done by stirring with a long spatula.
Shelf Life	The materials should be stored in the original unopened containers under cool dry conditions at temperatures between 10 and 25 °C. The shelf life is one year. Opened containers should be resealed.



Certificate No. GB14/92020



Certificate No. GB93/7985



ALH Systems Limited

1 Kingdom Avenue, Northacre Industrial Park, Westbury, Wiltshire BA13 4WE England
Telephone: (+44) 01373 858234 Email: sales@alh-systems.co.uk



Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. All Products should be used in accordance with your own COSHH Assessments. For additional health and safety information, call 01373 858234.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that ALH believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond ALH's control and uniquely within user's knowledge and control can affect the use and performance of an ALH product in a particular application. Given the variety of factors that can affect the use and performance of an ALH product, the user is solely responsible for evaluating the ALH product and determining whether it is fit for a particular purpose and suitable for the user's methods of application.

Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically state on the applicable ALH product packaging or product literature, ALH warrants that each ALH product meets the applicable ALH product specification at the time ALH ships the product. ALH MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONIDTION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the ALH product does not conform to this warranty, then the sole and exclusive remedy is, at ALH's option, replacement of the ALH product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, ALH will not be liable for any loss or damage arising from the ALH product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

11/07/2014



Certificate No. GB14/92020



Certificate No. GB93/7985