

1184-M SERIES

FLUORESCING WITH SECONDARY HEAT CURING CAPABILITIES

APPLICATIONS	FEATURES	BONDS	BIO-APPROVALS
? Sealing ? Conformal Coating of Medical Electronics	? Solvent-Free ? For Coating or Sealing ? Fluoresce For Visual or Automated Inspection	? CAP ? Polyurethane ? Polystyrene ? Steel ? SAN	? USP Class VI - Elution, Systemic Injection, Intracutaneous ? ISO 10993 - Intracutaneous, Systemic Injection, Muscle Implant, Cytotoxicity

INTRODUCTION

Dymax MD adhesives cure with UV and visible light. These adhesives increase productivity, lower assembly costs and enhance worker safety. When cured with Dymax MEDI-CURE[®] UV lamps, these adhesives provide optimum process flexibility. They allow the user to select the optimum combination of adhesive and cure mechanism to enhance process and performance requirements.

TYPICAL UNCURED PROPERTIES

Solvent Content	None - 100% Solids	
Composition	Urethane Oligomer/(Meth)Acrylate Monomer Blends	
Appearance	Clear/Straw Liquid	
Flash Point	>93°C (200°F)	
Solubility	Alcohol/Chlorinated Solvents	
Toxicity	Low	
Viscosity (20 rpm)	1184-M 400 cP (nominal)	ASTM D-1084
	1184-M-VLV 150 cP (nominal)	ASTM D-1084
	1184-M-VT 12,000 cP (nominal)	ASTM D-1084

TYPICAL CURED PROPERTIES

PHYSICAL

Durometer Hardness Range	D80	ASTM D-2240
Tensile at Break	6,200 psi	ASTM D-638
Elongation at Break	5%	ASTM D-638
Thermal Range (brittle/degrades)	-50° to 180°C (-55° to +350°F)	DSTM D-200*
Coefficient of Thermal Expansion	70 x 10 ⁻⁶ in/in °C	ASTM D-696
Water Absorption (24 h)	0.6%	ASTM D-570

*DSTM Refers to Dymax Standard Test Method

ELECTRICAL

Dielectric Strength	1,800 Volts/Mil	ASTM D-149
Dielectric Constant, 23°C, 1MHz	3.4	ASTM D-150
Dissipation Factor, 23°C, 1MHz	0.03	ASTM D-150
Volume Resistivity	3.6 x 10 ¹³ ? -cm	ASTM D-257
Surface Resistivity	3.8 x 10 ¹⁴ ?	ASTM D-257

STORAGE AND SHELF LIFE

Store in original, light blocking container. Do not expose to sunlight or any light source. These products have a one year shelf life when stored below 32°C (90°F) in original, unopened container.

BIOCOMPATIBILITY & STERILIZATION

SME Technical Paper #AS91-397, 1991 advises that "All adhesives are toxic in their raw or uncured state. Complete cure...is required to retain Class VI certification status." It is recommended that biocompatibility testing of the completed device be done following sterilization to eliminate the effects of minor process variations and contamination during assembly. The sterilization methods of choice are gamma irradiation and ethylene oxide. Sterilization by autoclaving may be limited to certain applications. Laboratory data indicates that gamma irradiation cures Dymax adhesives.

SAFETY

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the Material Safety Data Sheet before use.

© 1997, 1998 Dymax Corporation
MD² Medical Device Adhesives is also a registered trademark of Dymax Corporation

The data contained in this bulletin which represents typical results, is furnished for information only, and is believed to be reliable. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method mentioned herein and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use thereof. Nothing in this bulletin is to be interpreted as a representation of freedom from domination of patents owned by others or a license under a Dymax Corporation patent. We recommend that each prospective user test the proposed application before repetitive use, using the data as a guide. For specific information, refer to Material Safety Data Sheet before use.

TYPICAL LIGHT CURE DATA

Lamp	MC-5000	MC-4000	FUSION F-300 "D"
Light Type	UV/Visible	UV/Visible	UV/Visible
Lamp Type	5" x 5" Flood	3/16" Spot	1" x 10" Focused Beam
Maximum Lamp Intensity @ 365 nm	300 mW/cm ²	4000 mW/cm ²	8000+ mW/cm ²
Intensity @ Time Of Test @ 365 nm	150 mW/cm ²	1800 mW/cm ²	4000 mW/cm ²
Adhesive Absorption Range (nm)	300-500	300-500	300-500
Equipment Output Range (nm)	300-500	300-500	300-500
Cure Speed (Sec)			
Fixture Between Glass Slides	1	1	<1
Tack Free Surface Cure	15	15	5
Nominal Cure Depth (0.125")	>10	8	18
Cure Depth In 1 Minute (Inch)	0.140	0.35	>.250

The required intensity and cure time should be determined during the initial process validation stage. Factors that should be considered during process validation which can affect the adhesive cure rate and depth of cure include but are not limited to: the part geometry, bond-gap size, percent light transmission through the substrate at 365 nm and 436 nm, distance from the light source to the adhesive bond area, UV and visible light intensity and spectral output of the light source, the desired margin of safety to be built into the process and minimum and maximum exposure times.

HEAT CURE (AFTER UV CURING)

Heat may be used as a secondary cure for shadowed areas only after product has been cured with UV. The following is a guide and is dependent on the amount of material to be cured:

<u>Minimum Temperature</u>	<u>Time</u>
120°C (250°F)	30 minutes
135°C (275°F)	15 minutes

DISPENSING

BIOCOMPATIBILITY & STERILIZATION

SME Technical Paper #AS91-397, 1991 advises that "All adhesives are toxic in their raw or uncured state. Complete cure...is required to retain Class VI certification status." It is recommended that biocompatibility testing of the completed device be done following sterilization to eliminate the effects of minor process variations and contamination during assembly. The sterilization methods of choice are gamma irradiation and ethylene oxide. Sterilization by autoclaving may be limited to certain applications. Laboratory data indicates that gamma irradiation cures Dymax adhesives.

SAFETY

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the Material Safety Data Sheet before use.

© 1997, 1998 Dymax Corporation
MD² Medical Device Adhesives is also a registered trademark of Dymax Corporation

The data contained in this bulletin which represents typical results, is furnished for information only, and is believed to be reliable. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method mentioned herein and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use thereof. Nothing in this bulletin is to be interpreted as a representation of freedom from domination of patents owned by others or a license under a Dymax Corporation patent. We recommend that each prospective user test the proposed application before repetitive use, using the data as a guide. For specific information, refer to Material Safety Data Sheet before use.

Dymax 1184-M Series adhesives are available in various packages such as syringes, cartridges, bottles, and pails. They may be dispensed with a variety of automatic bench-top syringe applicators or other equipment as required. Any questions relating to dispensing and curing systems for specific applications should be referred to the Dymax Technical Center at (860) 482-1010.

BIOCOMPATIBILITY & STERILIZATION

SME Technical Paper #AS91-397, 1991 advises that "All adhesives are toxic in their raw or uncured state. Complete cure...is required to retain Class VI certification status." It is recommended that biocompatibility testing of the completed device be done following sterilization to eliminate the effects of minor process variations and contamination during assembly. The sterilization methods of choice are gamma irradiation and ethylene oxide. Sterilization by autoclaving may be limited to certain applications. Laboratory data indicates that gamma irradiation cures Dymax adhesives.

SAFETY

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the Material Safety Data Sheet before use.

© 1997, 1998 Dymax Corporation
MD² Medical Device Adhesives is also a registered trademark of Dymax Corporation

The data contained in this bulletin which represents typical results, is furnished for information only, and is believed to be reliable. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method mentioned herein and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use thereof. Nothing in this bulletin is to be interpreted as a representation of freedom from domination of patents owned by others or a license under a Dymax Corporation patent. We recommend that each prospective user test the proposed application before repetitive use, using the data as a guide. For specific information, refer to Material Safety Data Sheet before use.