



# Jet-melt™

## 3764 Adhesive

### Product Data Sheet

Updated : March 1996  
Supersedes : December 1993

#### Product Description

Jet-melt Adhesive 3764 is a plastics bonding hot melt adhesive with good impact resistance at low temperatures.

#### Physical Properties

Not for specification purposes

Base	EVA	
Colour	Clear	
Viscosity cP at 190°C <sub>1</sub>	6000	
Temperature Control Setting	4	
FDA Accepted <sub>2</sub>	Yes	
Sizes Available	26 x 73 mm for the Jet-melt Air Powered Applicator. 15 x 203 mm for the Jet-melt Touch Control Quadrack Applicator. 15 x 48 mm for the Jet-melt Touch Control Applicator. 12 x 300 mm for the Jet-melt All Electric Applicator.	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	
<sub>1</sub> Brookfield Thermosel Viscometer.		
<sub>2</sub> FDA Reg. 175.105 (adhesives) CFR Title 21.		

#### Performance

##### Characteristics

Not for specification purposes

<b>Delivery Rate for 26 x 73 mm slug</b>	55 seconds	
<b>Ball and Ring Softening Point</b> <sub>3</sub>	88 °C	
<b>Heat Resistance</b>	60 °C	
<b>Impact Resistance</b>	14 in/lbs at -18°C 58 in/lbs at 22°C	

Date : March 1996  
3764 Adhesive

### Performance Characteristics

Not for specification purposes

<b>Peel Strength at 22°C</b> 4	23 N/10mm	
<b>Shear Strength at 22°C</b> 5	2.7 MPa	
<b>Tensile Strength at 22°C</b>	4.5 MPa	
<b>Elongation</b>	625 %	
<b>Bonding Range</b> 3mm bead 6	40 seconds	
3 ASTM E-28-6-7. 4 On Canvas. 5 On Douglas Fir. 6 3mm semi circular bead, Douglas Fir to Douglas Fir.		

### Health and Safety Information

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.  
For information please contact your local 3M Office  
[www.3M.se](http://www.3M.se)

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.

3M, Jet-melt and Quadrack are trademarks of the 3M Company.



### 3M Svenska AB Industri

Bollstanäsvägen 3

191 89 Sollentuna

Tel: 08-92 22 50

Fax: 08-92 22 88

E-post: [kundservice@mmm.com](mailto:kundservice@mmm.com)

[www.3M.se/lim](http://www.3M.se/lim)