

Date: September 2017
Rev: V
No. of Components: Two
Mix Ratio by Weight: 100 : 5
Specific Gravity: Part A: 2.10 Part B: 1.05
Pot Life: 18 Hours
Shelf Life- Bulk: Six months at room temperature

Recommended Cure: 150°C / 1 Hour

Minimum Alternative Cure(s):

May not achieve performance properties listed below

150°C / 5 Minutes

120°C / 10 Minutes

100°C / 20 Minutes

80°C / 45 Minutes

NOTES:

- Container(s) should be kept closed when not in use.
- Filled systems should be stirred thoroughly before mixing and prior to use.
- Performance properties (rheology, conductivity, others) of the product may vary from those stated on the data sheet when bi-pak/syringe packaging or post-processing of any kind is performed. Epoxy's warranties shall not apply to any products that have been reprocessed or repackaged from Epoxy's delivered status/container into any other containers of any kind, including but not limited to syringes, bi-paks, cartridges, pouches, tubes, capsules, films or other packages.

Product Description: EPO-TEK® H24 is a two component, electrically and thermally conductive epoxy adhesive designed for semiconductor die attach and hybrid micro-electronics assembly.

Typical Properties: Cure condition: 150°C / 1 Hour Different batches, conditions & applications yield differing results.

Data below is not guaranteed. To be used as a guide only, not as a specification. * denotes test on lot acceptance basis

PHYSICAL PROPERTIES:

* Color (before cure):	Part A: Silver	Part B: Amber
* Consistency:	Smooth paste	
* Viscosity (23°C) @ 10 rpm:	15,000-23,000	cPs
Thixotropic Index:	1.9	
* Glass Transition Temp:	≥ 100	°C (Dynamic Cure: 20-200°C/ISO 25 Min; Ramp -10-200°C @20°C/Min)
Coefficient of Thermal Expansion (CTE):		
Below Tg:	28	x 10 ⁻⁶ in/in°C
Above Tg:	104	x 10 ⁻⁶ in/in°C
Shore D Hardness:	76	
Lap Shear @ 23°C:	> 2,000	psi
Die Shear @ 23°C:	≥ 5	Kg 1,778 psi
Degradation Temp:	470	°C
Weight Loss:		
@ 200°C:	0.04	%
@ 250°C:	0.04	%
@ 300°C:	0.10	%
Suggested Operating Temperature:	< 350	°C (Intermittent)
Storage Modulus:	484,807	psi
Ion Content:	Cl ⁻ : 60 ppm	Na ⁺ : 88 ppm
	NH ₄ ⁺ : 21 ppm	K ⁺ : 8 ppm
* Particle Size:	≤ 45	microns

ELECTRICAL AND THERMAL PROPERTIES:

Thermal Conductivity:	0.7	W/mK
* Volume Resistivity @ 23°C:	≤ 0.02	Ohm-cm

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.

EPOXY TECHNOLOGY, INC.

14 FORTUNE DRIVE, BILLERICA, MA 01821 (978) 667-3805, FAX (978) 663-9782

www.epotek.com

