



BETASEAL™ X2500 PLUS (A+B)

Glass Bonding Systems

BETASEAL™ X2500 PLUS (A+B) is a two-component polyurethane adhesive for glass and structural bonding applications. It has high viscosity and cures almost independently of moisture.

Product information

Colour	Black -
Solid content	≥95 %

Rheological properties

Viscosity, Ballan, 23°C, 4mm / 4bar	10 - 26 g/min
-------------------------------------	---------------

Cured properties

Stress at break	5 MPa	DIN 53504
Strain at break	200 %	DIN 53504
Lap shear strength, 3 days	≥4.5 MPa	DIN EN 1465

Storage and stability

Shelf life	9 ¹ months
------------	-----------------------

1: Shelf life is assured at +5°C to +25°C in unopened containers. Short time storage temperatures: 0°C to +40°C

Characteristics

Compatibility	Glass
---------------	-------



DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2020 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. The customer is solely responsible to determine whether DuPont products are suited for customer's intended purpose or application and may contact DuPont technical experts for more product details prior to sourcing products. DuPont disclaims liability for any incidental or consequential damages resulting from customer's use of DuPont products. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-4 and DuPont CAUTION Regarding Medical Applications H-50102-4.