

Merbenit SK212 ADV

Elastic adhesive with high initial adhesion and high strength. Specially developed for windscreen replacement and general bonding of windows in cabins and vehicles, certified according to FMVSS 212, easy to process.

Product advantages

- Very high initial adhesion, correctable
- Without the addition of solvents, isocyanates, silicones, phthalates
- Very good sealing properties
- Very wide adhesion range
- Low odour
- Paint compatible
- Resistant to powder and thermal coating providing short-time resistance up to +200°C
- Non-corrosive on surfaces
- Impact and vibration-resistant (shock-absorbing)
- High electrical resistance, suitable for aluminium car bodies, vehicles equipped with GPS or assistance systems

Technical data

Chemical base	Silane modified polymer
Mechanism of curing	1 comp. moisture curing
Consistency	stable
Tooling time	max. 15 min.
Curing rate after 24h	ca. 2.5 mm
Curing rate after 48h	ca. 4.0 mm
Shore-A-hardness, DIN ISO 48-4	ca. 60
Tensile strength DIN 53504 S2*	ca. 3.5 N/mm ²
Modulus elongation at 100%, DIN 53504 S2 *	ca. 2.3 N/mm ²
Elongation at break, DIN 53504 S2 *	ca. 225%
Shear strength	ca. 2.9 N/mm ²
Density	1.41 ± 0.05 g/cm ³
Volume change, DIN EN ISO 10563	≤ 4%
Temperature resistance after curing	- 40 °C to + 90 °C
Application temperature	+ 5 °C to + 40 °C
Initial Tack	5600 Pa
Volume resistivity p, DIN EN 62631-3-1	10 ¹¹ Ω*cm

All measurements were performed under normal conditions (23 °C and 50 % relative humidity).

* The data are based on measurements after 3 months.

Application

Bonding of panes in vehicle, carriage and cabin construction. Bondings that cannot be supported and require rapid further processing. Flexible, immediately load-bearing bondings in the fields of metal, apparatus and mechanical engineering, plastics, ventilation and air-conditioning technology, bodywork, carriage, vehicle and container construction.

Substrate range

Suitable materials include metals, thermal coated, painted, galvanised, anodised, chromated or hot-dip galvanised surfaces, various plastics, ceramics, concrete, plaster, wood, glass, painted surfaces, etc. Due to the wide variety of different plastics and compositions, as well as materials that are prone to stress cracking (PC, PMMA), preliminary tests are recommended. Please also refer to the section on primers.

Materials that are not suitable include PP, PE, PTFE (Teflon), silicones, bituminous substrates.

In case of high temperatures of metal profiles, deck strips or copper deck strips exposed to the sun, our neutral-curing silicones Gomastit 400 and Gomastit 407 are ideal.

Preliminary tests are always recommended for unknown applications!

Meets the standards and certificates

- EMICODE EC1Plus
- Eurofins IAC Gold
- FMVSS 212 60' drive away time

Technical data sheet Merbenit SK212 ADV

Substrate preparation

To achieve reproducible results the substrate has to be pretreated according to the state of technology. All undefined surfaces must be removed using suitable methods. Apply the adhesive/sealant promptly to the prepared surface. Depending on the substrate and the expected requirements a mechanical or chemical pre-treatment is recommended respectively cleaning with rubbing alcohol, isopropyl or acetone. For application the surface has to be clean, durable and free of dust, oil and grease. The compatibility with adjacent materials, coatings etc. must be determined in advance.

Primer

With many materials, good adhesion is achieved without primer. Preliminary tests are recommended. Primers can be used to improve adhesion:

- on porous, absorbent surfaces such as concrete, masonry, plaster: Apply V21 primer with a brush. The use of V21 primer is generally recommended when exposed to water.
 - on smooth, non-absorbent surfaces such as plastic, stainless steel, thermal coating: Apply a thin layer of V40 primer with a lint-free cloth. As thermal coatings can vary greatly, the use of V40 primer or preliminary tests are generally recommended.
 - on UV-exposed glass: Black Glass primers serve as a protective barrier against the effects of UV radiation.
 - In direct contact with bituminous substrates, V17 primer can be used as a barrier layer.
 - please observe the drying times and information on the packaging of the respective primers or in the respective technical data sheets at www.merz-benteli.ch -> Accessories.
- Primers are sensitive to moisture. Close the packaging immediately after use and use up as quickly as possible.
- Note: primers and thinly applied sealants leave stains that cannot be completely removed.

Processing

- Can be applied directly from the cartridge / bag using a suitable caulking gun (manual, air, battery)
- Cut the nozzle tip according to the joint width V-nozzles are recommended for bonding applications
- Depending on the bonding surface, material expansion, tension and mechanical stresses a layer thickness of 1 - 6 mm is recommended
- For vapour permeable substrates the material can be applied in a large area using a notched trowel
- Can be applied with automatic dispensing equipment
- Non-cured adhesive can be removed with rubbing alcohol or isopropyl
- Cured adhesive can only be removed mechanically

Paint compatibility

Due to the wide variety of varnishes and paints on the market, we recommend preliminary tests. Delayed drying may occur with alkyd resin paints. If applied to painted or plastered surfaces, the paint/plaster must be allowed to dry sufficiently (usually 10 days). Movement-compensating sealants with greater elasticity than paint must not be painted over completely (cracking).

Chemical resistance

- Good resistance to water, sea water, aliphatic solvents, oils, greases, diluted inorganic acids and alkalis
- Moderate resistance to esters, ketones and aromatic compounds
- Not resistant to concentrated acids and chlorinated hydrocarbons, gasoline, petrol oil

The chemical resistance depends on the exposure time, temperature and concentration of the chemical. Preliminary tests under practical conditions are therefore highly recommended. Our data sheets on chemical resistance contain further information.

Colours

- black

Packaging

- Cartridges of 290 ml in boxes of 12 units
- Sausages of 600 ml in boxes of 12 units

Shelf life and storage conditions

- 15 months from date of production in original packaging
- Store cool and dry (10 - 25 °C)
- Further information on request

Work and environmental safety

Important information about work and environmental safety is available on the material safety data sheet.

merz+benteli ag

Freiburgstrasse 616
CH - 3172 Niederwangen
Phone +41 31 980 48 48
Fax +41 31 980 48 49
info@merz-benteli.ch
www.merz-benteli.ch

Our information is based on experiences in lab and practice. Their publication occurs, however, without takeover of a liability for damages and losses which are to be put down to these information, as there the practical application conditions are lying outside of the enterprise's control. The user is not released from the necessity to carry out own attempts for the planned applications under practical conditions. Due to the different materials, processing methods and local factors onto which we have no influence, no guarantee – also in patent-legal respect – can be taken over. We recommend therefore sufficient own attempts. By the way we refer to our General Business Conditions. Technical characteristics according to the Technical Data Sheets up to their expiry date which is available upon request and which is available on our website. Technical changes reserved. Contents examined and released by merz+benteli ag, CH - Niederwangen/Berne

