



TECHNICAL DATA

RESIN PACK 14C

Product Description

Resin Pack 14C is a two component polyurethane compound specifically formulated for use as a sealant against the ingress of moisture and gas into telecommunications cable ducting.

Features

- * Fully complies with BT Specification M229C
- * Supplied in a 250 ml “universal” cartridge fitted with a static mixer nozzle
- * Bonds well to Polyethylene, Polycarbonate and PVCu
- * Rapid cure
- * Improved re-enterable characteristics as compared to Resin Pack 14B

Typical Uncured Physical Properties

Property	Base	Hardener
Viscosity (mPas)	500	500
Colour	Black	Brown
Specific Gravity	1.02	1.18
Mix Ratio (by weight)	1	1.16
(by volume)	1	1

Note: The above technical information and data should be considered representative or typical only and should not be used for specification purposes.



RESULTS OF RESIN PACK 14C TESTED AGAINST BT SPECIFICATION M229C

CLAUSE	TEST	SPEC REQUIREMENT	RESULTS
4.1.1.	Mixing Time	Homogenous mix achieved and contents dispensed within two minutes	As spec requires
4.1.2.	Effect on cable sheath	Shall not adversely affect polyethylene	No adverse effect on polyethylene
4.1.3.	Phenyl Isocyanate concentration	Must not exceed 0.01%	Less than 0.0005%
4.2.1.	Viscosity	20,000 - 25,000 mPas	20,500 mPas
4.2.2.	Gel Time	10 minutes	6 minutes
4.2.3.	Max. Temp.	120°C	50°C
4.2.5.	Stress crack on Polyethylene	No stress crack	No stress crack
4.2.6.	Cure/Setting	Tack free inside 1 hour @ 20°C	Tack free 10 minutes
	"	Acceptable cure after 24 hours @ 5°C	Good cure after 24 hours @ 5°C
4.2.7.	Adhesion to PVC	Minimum 0.25 N/mm ²	0.32 N/mm ²
4.2.8.	Hardness @ 24 Hours	50 - 70 IRHD	65 IRHD
4.2.9.	Compressive Strength	Min. 2 N/mm ²	2.5 N/mm ²
4.2.10.	Moisture Resistance	No foaming	No foaming
4.2.11.	Seal Ability	No water loss	No water loss



Directions for use

See instruction leaflet in kit.

Surface Preparation

Cables and ducts should be prepared as per instructions.

Storage and Shelf Life

18 months at 5-25°C.



Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. All Products should be used in accordance with your own COSHH Assessments. For additional health and safety information, call 01373 858234.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that ALH believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond ALH's control and uniquely within user's knowledge and control can affect the use and performance of an ALH product in a particular application. Given the variety of factors that can affect the use and performance of an ALH product, the user is solely responsible for evaluating the ALH product and determining whether it is fit for a particular purpose and suitable for the user's methods of application.

Warranty, Limited Remedy and Disclaimer

Unless an additional warranty is specifically state on the applicable ALH product packaging or product literature, ALH warrants that each ALH product meets the applicable ALH product specification at the time ALH ships the product. ALH MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the ALH product does not conform to this warranty, then the sole and exclusive remedy is, at ALH's option, replacement of the ALH product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, ALH will not be liable for any loss or damage arising from the ALH product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

Version: 2

Date: August 2019