



Scotch-Weld™

Spray 76 High Tack Adhesive

Product Data Sheet

Updated : February 2011

Supersedes : December 2007

Product Description

Spray 76 Adhesive is an aerosol adhesive which has the advantage of non-misting lace spray pattern. The adjustable spray tip allows for selection of spray width and delivery rate. The defined edge of the lace spray pattern permits accurate and economical application.

The adhesive develops tack quickly, has one hour bonding range for two surface application, and dries to give high strength bonds which have excellent resistance to water and long term ageing.

Physical Properties

Not for specification purposes

Solvent	Cyclohexane and Pentane	
Flash Point	Below -41°C	
Propellant	Dimethyl Ether	
Consistency	Thin Liquid in Aerosol	
Solids Content	13% approx.	
Colour	Clear/Pale Cream	
Shelf Life	12 months from date of receipt by customer when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance

Characteristics

Not for specification purposes

Service Temperature Range	-32°C to +80°C	
Water Resistance	Good	
Weathering Resistance	Good	
Fuel and Oil Resistance	Poor	

Strength of Adhesive

Test Results

180° Peel strength. Canvas (No. 10 Cotton Duck) was bonded to the following substrates. Both surfaces were coated, bonds were made at a 5 minutes open time, and dried one day at 24°C and 3 days at 50°C. Bonds were then pulled in 180° peel at a rate of 50mm per minute.

Spray 76 High Tack Adhesive

Substrate	180° Peel Strength N/cm
Aluminium	47 - 51
Cold Rolled Steel	47
Polypropylene	47 - 55
Polyethylene	20 - 24
ABS	39 - 47
Nylon	26
PVC	51 - 59
Perspex	35 - 43
Polycarbonate	43 - 51
Butyl Rubber	10 - 14
EPDM Rubber	14 - 17
Natural Rubber	10 - 13
Neoprene Rubber	10 - 14
Nitrile Rubber	7 - 10
SBR	7 - 9

Additional Product Information

Coverage: Approximately 3.7 square metres per container.
Approximate Drying or Setting Time: Between 10-60 minutes.
Application Temperature Range: 16°C to 27°C

Storage Conditions

Store at 23°C for optimum shelf life.

Applications

Bonds paper, felt, fabric, cork, cardboard, rubber and plastics to themselves, metal, wood, glass etc.
 Suitable for bonding supported vinyl (P.V.C.) but should be checked for plasticiser migration.
 Spray 76 Adhesive is widely used for bonding polypropylene and polyethylene films to themselves and other substrates.

Directions for Use

Ensure that all surfaces to be bonded are clean, dry and free from dust, oil or grease before application of adhesive.

Ensure that the nozzle points away from all persons and towards the surface to be sprayed. Select the spray pattern required by turning the nozzle between the "L" and "H" positions indicated on the plastic collar. Do not try to force the nozzle beyond these settings. This also changes the spray pattern width as follows:

Low Setting = approx 2cm wide.

High Setting = approx 7cm wide.

Shake the can well before using, 5-10 seconds should be sufficient.

Hold the can between 12-18 cm from the surface to be sprayed. A narrowing of the pattern will occur if held more than 20 cm from the surface to be sprayed. When spraying, depress nozzle fully to avoid spluttering or dripping of adhesive.

For lightweight materials it is usually only necessary to coat one surface, the least porous bonds can be made up to 10 minutes after application.

Where higher strength is required or heavier materials have to be bonded, apply adhesive to both surfaces. On some substrates, bonds can be made up to 60 minutes after application. Under normal circumstances apply Spray Adhesive 76 to both surfaces, allow adhesive to dry for a few minutes until aggressively tacky, and make bond using firm pressure.

To prevent nozzle from blocking, at the end of each day turn the can upside down and press tip until the spray is clear from adhesive, and wipe tip.

Clean Up:

Spray nozzle or excess material may be cleaned with Scotch-Weld Solvent No. 1. **NOTE:** Solvent No. 1 is highly flammable. When using solvents for clean up it is essential that proper safety precautions are observed.

Health & Safety Information

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.
For information please contact your local 3M Office. 3M Svenska AB, Industri, 191 89 Sollentuna
www.3M.se

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law

3M and Scotch-Weld are trademarks of the 3M Company.



3M Svenska AB
Industri
Bollstanäsvägen 3
191 89 Sollentuna
Tel: 08-92 22 50
Fax: 08-92 22 88
E-post: kundservice@mmm.com
www.3M.se/tejp