

DESCRIPTION

- Three-part, optically clear, pourable silicone system
- 1:1:0.1 Mix Ratio (Part A:B:C)
- Incorporates an adhesion promoter to help adhere to polycarbonate and other difficult substrates
- Offers excellent physical properties and a broad operating temperature range

APPLICATION

- As an adhesive or encapsulant for applications requiring optical clarity and a 1.46 refractive index
- Use as an optical coupling agent, as a lens sealing material, or for other photonics applications including HBLED's, photo detectors, lasers, discrete optics and flat panel displays

PROPERTIES

| TYPICAL PROPERTIES | AVERAGE RESULT | STANDARD | NT-TM |
|--------------------------------------|--------------------|------------------------|-------|
| Uncured: | | | |
| Appearance | Translucent | ASTM D2090 | 002 |
| Viscosity, Part A | 48,500 cP | ASTM D1084, ASTM D2196 | 001 |
| Viscosity, Part B | 40,000 cP | ASTM D1084, ASTM D2196 | 001 |
| Viscosity, Part C | 1,350 cP | ASTM D1084, ASTM D2196 | 001 |
| Refractive Index | 1.46 | ASTM D1747, ASTM D1218 | 018 |
| Volatility | 0.8 % | ASTM D2288 | 004 |
| Tack-Free Time | 1 hour | ASTM C679 | 005 |
| Cured: 30 min @ 150°C (302°F) | | | |
| Specific Gravity | 1.14 | ASTM D792 | 003 |
| Durometer, Type A | 20 | ASTM D2240 | 006 |
| Tensile Strength | 550 psi (3.79 MPa) | ASTM D412 | 007 |
| Elongation | 325 % | ASTM D412 | 007 |

| TYPICAL PROPERTIES | AVERAGE RESULT | STANDARD | NT-TM |
|----------------------|--------------------|-----------|-------|
| Stress @ 100% strain | 70 psi (0.48 MPa) | ASTM D412 | 007 |
| Tear Strength | 25 pli (4.41 kN/m) | ASTM D624 | 009 |

INSTRUCTIONS FOR USE

Mixing

Mix in a ratio of 1:1:0.1, Part A: Part B: Part C. If mixing by hand, take care to minimize air entrapment while mixing.

Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches Hg, to a container rated for use and of volume at least four times that of material being deaerated. Hold vacuum until presence of air is no longer evident.

Substrate Consideration

Cures in contact with most materials common to electronic assemblies. Exceptions include butyl and chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents. Units being encapsulated or potted should be clean and free of surface contaminants. Containers and dispensers should also be clean and dry. Prevent cure inhibition by washing all containers with clean solvent or volatilizing the contaminants by heat.

Note: Some bonding applications may require the use of a primer. NuSil Technology LLC CF1-135 silicone primer is recommended.

Adjustable Cure Schedule

Product cures at room temperature and a wide range of elevated temperatures and cure times to accommodate different production needs. Contact NuSil Technology LLC for details.

Packaging

50 Gram Kit
2 Pint Kit (958 g)
2 Gallon Kit (7.65 kg)

Warranty

12 Months

WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology LLC believes that the information and data contained herein are accurate and reliable. However, the user is responsible to determine the material's suitability and safety of use. NuSil Technology LLC cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology LLC makes no warranty concerning fitness for any use or purpose. NuSil Technology LLC has completed no testing to establish safety of use in any medical application.

NuSil Technology LLC has tested this material only to determine if the product meets the applicable specifications. (Please contact NuSil Technology LLC for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology LLC



products in a particular application, review the latest Material Safety Data Sheet and contact NuSil Technology LLC with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, obtain available product safety information and take the necessary steps to ensure safety of use.

SPECIFICATIONS

Do not use the typical properties shown in this technical profile as a basis for preparing specifications. Please contact NuSil Technology LLC for assistance and recommendations in establishing particular specifications.

PATENT WARNING

NuSil Technology LLC disclaims any expressed or implied warranty against the infringement of any patent. NuSil Technology LLC does not warrant the use or sale of the products described herein will not infringe the claims of any United States' or other country's patents covering the product itself, its use in combination with other products or its use in the operation of any process.

WARRANTY INFORMATION

NuSil Technology LLC's warranty period is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology LLC provides a specific written warranty of fitness for a particular use, NuSil Technology LLC's sole warranty is that the product will meet NuSil Technology LLC's then current specification. NuSil Technology LLC specifically disclaims any other expressed or implied warranty, including warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology LLC's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. NuSil Technology LLC expressly disclaims any liability for incidental or consequential damages.